


Lewabrane® RO S440 HF elements are spiral-wound, composite polyamide membrane elements designed for the desalination of seawater. The S440 HF membrane is characterized by an extremely durable, highly cross-linked polymeric separating layer suitable for high salinity, high pressure applications. The Lewabrane® RO S440 HF is recommended for single pass and two pass applications (depending on the salinity, temperature, and permeate quality requirement) where stable salt rejection performance over the expected lifetime is an important consideration.

General Information

	Metric units	US units
Feed spacer thickness	0.7 mm	28 mil
Membrane area	40.9 m ²	440 ft ²
Salt rejection, av.	99.8 %	99.8 %
Salt rejection, min.	99.5 %	99.5 %
Boron rejection, typical	92.0 %	92.0 %
Permeate flow rate, av.	37.5 m ³ /d	9900 gpd
Permeate flow rate, min.	30.0 m ³ /d	7920 gpd

Element is tested under the following conditions: applied pressure 800 psi (55.2 bar), NaCl concentration 32,000 mg/l (or when tested on a mixed solution of 32,000 mg/l NaCl and 5 mg/l Boron), operating temperature 77 °F (25 °C), pH 8 and recovery rate 8 %.

Element Dimension



	A (Length)	B (Diameter)	C (ID)
Metric Units	1016 mm	201 mm	29 mm
US Units	40 inch	7.9 inch	1.125 inch

Application Data

	Metric units	US units
Operating pressure, max.	83 bar	1200 psi
Operating temperature, max.	45°C	113°F
Feed water SDI, max.	5	5
pH range during operating	2 - 11	2 - 11
pH range during cleaning	1 - 12	1 - 12
Pressure drop per element, max.	1.0 bar	15 psi
Pressure drop per vessel, max.	3.5 bar	50 psi
Chlorine concentration, max.	0.1 ppm	0.1 ppm

As with any product, use of the products mentioned in this publication in a given application must be tested (including field testing, etc.) by the user in advance to determine suitability.

Additional Information

- Treat RO Elements with care; do not drop the element.
- Each RO Element is wet tested, preserved in a 1% weight sodium bisulfite solution, and vacuum packed in oxygen barrier bags.
- During storage, avoid freezing and direct sunlight. The temperature should be below 35 °C (95 °F).

After Installation

- Keep the RO Elements wet, and use a compatible preservative for storage duration longer than 7 days.
- During the initial start up, discharge the first permeate to drain for 30 min.
- Permeate back pressure should not exceed feed pressure at any time.
- The RO Elements shall be maintained in a clean condition, unfouled by particulate matter or precipitates or biological growth.
- Consider cleaning, if the pressure drop increases by 20% or water permeability decreases by 10%.
- Use only chemicals which are compatible with the membrane.
- For additional information consult the Lewabrane® technical information available at www.lpt.lanxess.com.

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the LANXESS Sybron Chemicals Inc. products mentioned in this publication. For materials mentioned which are not LANXESS Sybron Chemicals Inc. products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms. Consult your LANXESS Sybron Chemicals Inc. representative or contact the Product Safety and Regulatory Affairs Department at LANXESS Corporation at 1-800-526-9377.

LANXESS Sybron Chemicals Inc.
www.lpt.lanxess.com
www.lanxess.com
www.US.lanxess.com

Contact:
200 Birmingham Road
Birmingham, NJ 08011

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

NOTE: The information contained in this publication is current as of the edition date. Please contact LANXESS Sybron Chemicals Inc. to determine if this publication has been revised.